

AD-A143 028


EFFECTS OF CYCLOHEXYL GROUPS AND ORTHO-SUBSTITUENTS ON  
THE VISCOSITY OF E. (U) HUGHES RESEARCH LABS MALIBU CA  
J D MARGERUM ET AL. JUN 84 HRL-TR-3 N00014-82-C-0512


1/1

UNCLASSIFIED

F/G 7/4

NL





MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A143 028

(12)

OFFICE OF NAVAL RESEARCH  
Contract N00014-82-C-0512

TECHNICAL REPORT NO. 3

EFFECTS OF CYCLOHEXYL GROUPS AND ORTHO-SUBSTITUENTS ON THE  
VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

by

J.D. Margerum, S.-M. Wong, J.E. Jensen,  
C.I. van Ast, and A.M. Lackner

To Be Presented at the Tenth International Liquid Crystal Conference,  
York, U.K., July 15-21, 1984

Hughes Research Laboratories  
3011 Malibu Canyon Road  
Malibu, CA 90265

June 1984


DTIC  
ELECTE  
JUL 12 1984  
A

DTIC FILE COPY

Reproduction in whole or in part is permitted for any purpose  
of the United States Government

Approved for Public Release; Distribution Unlimited

84 07 11 005



UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 3	2. GOVT ACCESSION NO. AD-A143028	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Effects of Cyclohexyl Groups and Ortho-Substituents on the Viscosity of Ester Liquid Crystal Components		5. TYPE OF REPORT & PERIOD COVERED Technical
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) J.D. Margerum, S.-M. Wong, J.E. Jensen, C.I. van Ast, and A.M. Lackner		8. CONTRACT OR GRANT NUMBER(s) N00014-82-C-0512
9. PERFORMING ORGANIZATION NAME AND ADDRESS Hughes Research Laboratories 3011 Malibu Canyon Road Malibu, CA 90265		10. PROGRAM ELEMENT PROJECT TASK AREA & WORK UNIT NUMBERS NR 051-818
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research/Chemistry Program Code 472 Arlington, VA 22217		12. REPORT DATE June 1984
		13. NUMBER OF PAGES 18
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES To Be presented at the 10th International Liquid Crystal Conference, York, U.K., July 15-21, 1984		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Nematic liquid crystals Class values of viscosity Cyclohexyl position effects Ester liquid crystal mixtures		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Structural effects on the relative viscosity of liquid crystal ester components are studied by capillary flow viscosity measurements of each component as an additive (10 to 25%) in a standard nematic mixture of short length 4-alkoxyphenyl 4-alkylbenzoates. An approximate class viscosity at 25°C is calculated and assigned to each additive component, indicative of its viscosity contribution in the environment of the phenyl benzoate mixture. Studies are made		

UNCLASSIFIED


SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

→ on the viscosity effects of replacing benzene rings with cyclohexane rings, and of using various ortho-substituents on phenyl groups. All of the additive components are esters or thioesters, including several newly synthesized compounds. The effect of a cyclohexyl group is strongly dependent on its position in the structure. The class viscosity values show a large decrease when cyclohexanecarboxylate replaces benzoate, only a modest decrease when cyclohexylbenzoate replaces biphenylcarboxylate, and a slight increase when a cyclohexyl ester replaces a phenyl ester. Although o-groups can be used effectively to alter the dielectric anisotropy and modify the nematic range of a component, they increase the class viscosity values substantially, with the magnitude of the viscosity effect in the following approximate order from several o-groups: Br > CN > CH<sub>3</sub> > pyridyl > Cl.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

NTIS GRA&I  
DTIC TAB  
Unannounced  
Justification



By \_\_\_\_\_  
Distribution/ \_\_\_\_\_  
Availability Codes \_\_\_\_\_  
Dist \_\_\_\_\_ Special \_\_\_\_\_

H1

EFFECTS OF CYCLOHEXYL GROUPS AND  
ORTHO-SUBSTITUENTS ON THE VISCOSITY OF ESTER  
LIQUID CRYSTAL COMPONENTS\*

J. D. MARGERUM, S.-M. WONG, J. E. JENSEN,  
C. I. VAN AST, AND A. M. LACKNER  
Hughes Research Laboratories  
3011 Malibu Canyon Road  
Malibu, California 90265, USA

Structural effects on the relative viscosity of liquid crystal ester components are studied by capillary flow viscosity measurements of each component as an additive (10 to 25%) in a standard nematic mixture of short length 4-alkoxyphenyl 4-alkylbenzoates. An approximate class viscosity at 25°C is calculated and assigned to each additive component, indicative of its viscosity contribution in the environment of the phenyl benzoate mixture. Studies are made on the viscosity effects of replacing benzene rings with cyclohexane rings, and of using various ortho-substituents on phenyl groups. All of the additive components are esters or thioesters, including several newly synthesized compounds. The effect of a cyclohexyl group is strongly dependent on its position in the structure. The class viscosity values show a large decrease when cyclohexanecarboxylate replaces benzoate, only a modest decrease when cyclohexylbenzoate replaces biphenylcarboxylate, and a slight increase when a cyclohexyl ester replaces a phenyl ester. Although o-groups can be used effectively to alter the dielectric

\*Presented at the Tenth International Liquid Crystal Conference, York, U. K., July 15-21, 1984.

J. D. MARGERUM, S. -M. WONG, et al

anisotropy and modify the nematic range of a component, they increase the class viscosity values substantially, with the magnitude of the viscosity effect in the following approximate order from several o-groups:  
 $\text{Br} > \text{CN} > \text{CH}_3 > \text{pyridyl} > \text{Cl}.$

## 1. INTRODUCTION

The effects of chemical structure on liquid crystal (LC) viscosity ( $\eta$ ) are important considerations in the selection of components for nematic mixtures used in display applications. For example, it is desirable to be able to predict the viscosity of a new multicomponent LC mixture accurately enough to decide whether or not it is worthwhile to make up a calculated eutectic mixture for study. We have previously described the assignment of approximate class viscosity values ( $\eta_{\text{class}}$ ) to eighteen different classes of ester LC structures<sup>1</sup>, and we have shown that these  $\eta_{\text{class}}$  values are useful in predicting the viscosity of new mixtures.<sup>1,2</sup> We are particularly interested in developing additional new LC mixtures with low viscosity, negative dielectric anisotropy, and wide nematic temperature range for both dynamic scattering and field-effect display applications. In working toward these goals, we report here more detailed studies on the viscosity effect of structural changes in LC esters in which phenyl groups are replaced by cyclohexyl groups, or in which o-substituents are used on phenyl

## VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

groups. Twenty additional ester structures are assigned  $\eta_{\text{class}}$  values, and systematic comparisons are made on the changes in class viscosities with structural variations.

### 2. EXPERIMENTAL

Flow viscosity studies are made with 29 different ester LC components. These are studied as additives in a standard mixture (HRL-2N42) of five 4-alkoxyphenyl 4-alkylbenzoate esters.<sup>1,2,3</sup> The capillary flow viscosity and density data are taken at 25°C with 10 to 25 mole percent of the components added to HRL-2N42, as previously described.<sup>1</sup> The code symbols used here for the individual compounds and their general classes are similar to those defined previously.<sup>1-5</sup> In our code a dash, -, is for the central phenyl benzoate structure, with alternate central structures represented by S for phenyl thiobenzoate, -[C] for phenyl cyclohexanecarboxylate, [C]- for cyclohexyl benzoate, [C]-[C] for cyclohexyl cyclohexanecarboxylate, and [Py]- for *o*-pyridyl benzoate. Additional rings in the structure are represented by P for phenyl and Y for cyclohexyl, while only *o*-substituents are shown in parenthesis, e.g. 1(Br)-Y3 stands for *o*-bromo-*p*-tolyl *p*-(4-propylcyclohexyl)benzoate. Twenty of the 29 LC compounds investigated are synthesized, and the other nine are commercial samples obtained from either E. Merck or from Atomergic Chemetals.

J. D. MARGERUM, S. -M. WONG, et al

Nineteen of the synthesized esters are prepared by reacting purified samples of commercially available (Aldrich) phenols or thiophenols with acid chlorides, whose acid intermediates are obtained by hydrolysis of the corresponding nitrile LC compounds (E. Merck). The other di-ester (4-OOCY4) is made using intermediates prepared as described before, namely the mono-ester 4-OH phenol<sup>1</sup> and the trans-4-butylcyclohexanecarbonyl chloride.<sup>4</sup> Thermal analysis data on the melting point (mp), clearpoint (clpt), and molar heat of fusion ( $\Delta H_f$ ) of the new compounds are obtained by differential scanning calorimetry.<sup>3</sup> The purity of all of the LCs is checked by thin layer chromatography and by liquid chromatography.<sup>1-3</sup>

### 3. RESULT AND DISCUSSION

#### 3.1 LC Compounds Synthesized

The abbreviation code, structure, melting point, clearpoint, and molar heat of fusion of the 20 LC compounds synthesized are given in Table I. The first 10 of these are all variations of similar three ring structures with the same alkyl end groups (e.g. 1-P3, 1SP3, 1-Y3, etc) and essentially the same molecular length. These structural variations are chosen not only to observe the viscosity effects of thioesters,

# VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

Table I. New LC Components Synthesized

CODE	STRUCTURE	mp (°C)	C <sub>1</sub> pt. (°C)	$\Delta H_f$ (kcal/mole)
1-P3		126	199	7.26
1-S-P3		126	235	6.12
1-Y3		121	188	5.84
1-S-Y3		120	224	4.72
1(CH <sub>3</sub> )-Y3		79	118	5.18
1(Br)-Y3		97	119	7.12
1(C)-P3		94	126	4.89
1(C)-Y3		91	129	6.35
1-[C]-Y3		53(96) <sup>a</sup>	204	5.93
1[C]-[C]-Y3		67(129) <sup>a</sup>	153	7.72
2-Y3		104	175	5.13
2-Y5		92	172	6.32
4-Y3		92	174	5.33
4-OOCY4		62(65) <sup>a</sup>	185	7.27
20-P3		128	235	7.88
20-P5		126	220	6.08
20-Y3		127	223	6.39
20-Y5		106	215	6.39
[P <sub>v</sub> ]-P05		78(86) <sup>a</sup>	114	3.65
[P <sub>v</sub> ]-[C]-Y3		108	118	8.51

<sup>a</sup> SMECTIC TO NEMATIC TRANSITION

cyclohexane groups, and o-substituents, but also to note these structural effects on the nematic temperature range, the birefringence ( $\Delta n$ ), and the dielectric anisotropy ( $\Delta \epsilon$ ). Studies on  $\Delta n$  and  $\Delta \epsilon$  are reported for several of these components in a recent paper.<sup>2</sup> The phenyl thiobenzoate derivatives, 1SP3 and 1SY3, have substantially higher clearpoint and about the same melting point as their corresponding phenyl benzoates, 1-P3 and 1-Y3. These thiobenzoates also have higher  $\Delta n$  and more positive  $\Delta \epsilon$  values than the benzoates.<sup>2</sup> The two o-substituted phenyl benzoates of this group, 1(CH<sub>3</sub>)-Y3 and 1(Br)-Y3, each have a lower melting point and clearpoint than either 1-P3 or 1-Y3. The o-substituents also have a large effect on  $\Delta \epsilon$ , with 1(CH<sub>3</sub>)-Y3 more positive and 1(Br)-Y3 much more negative in  $\Delta \epsilon$  than the unsubstituted R-YR' structures.<sup>2</sup> The cyclohexyl benzoate derivatives 1[C]-P3 and 1[C]-Y3 each have a lower melting point and clearpoint than 1-P3 and 1-Y3. In general, the replacement of a biphenylcarboxylate by a cyclohexylbenzoate has little effect on the nematic range, e.g. each of the following pairs have similar nematic ranges: 1-P3 and 1-Y3, 20-P3 and 20-Y3, 1[C]-P3 and 1[C]-Y3. However, the bicyclohexylcarboxylate structures, 1-[C]Y3 and 1[C]-[C]Y3, do have substantially lower melting points than these other structures.

## VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

### 3.2 Viscosity Measurements and Calculations

The flow viscosity measurements and calculated results are summarized in Table II. The LC components are all studied at 25°C as additives to the RO-R' mixture HRL-2N42, which is a five-component eutectic mixture<sup>1,2,3</sup> of 10-1, 20-3, 20-5, 40-1, and 40-3. The observed viscosity of this RO-R' mixture with x mole fraction of the additive(s) is used to estimate the approximate viscosity contribution of the additive ( $\eta_{calc}$ ) by applying equation 1 at the average molecular length ( $\bar{L}$ ) of the overall mixture:

$$\eta_{obs} = \eta_{calc} (x) + \eta_{RO-R'} (1-x) \quad (1)$$

The host viscosity value  $\eta_{RO-R'}$  is assumed to vary linearly with the  $\bar{L}$  of the overall mixture, as noted previously<sup>1</sup>, and the values are taken from equation 2.

$$\eta_{RO-R'} = 32.5 + 1.54 (\bar{L}-20) \quad (2)$$

This provides a small correction for differences in the molecular lengths of the additive. The class value of viscosity for each type of structure is assigned from the  $\eta_{calc}$  values obtained from components of each class.

The  $\eta_{calc}$  values are extrapolations which are assumed to correspond to the relative

J. D. MARGERUM, S. -M. WONG, et al

Table II. Viscosity Measurements and Calculated Component Viscosity<sup>a</sup>

Code	Source <sup>b</sup>	Length (Å)	Mixed In HRL-2N42		$\eta_{calc}$ (cP)	
			$\bar{r}$ (Å)	$\eta_{25}$ (cP)		
1-P3	I	21.45	10	20.50	33.23	81
1SP3	I	21.80	10	20.74	33.23	79
1-Y3	I	22.68	10	20.62	37.75	69
1SY3	I	22.53	10	20.60	36.27	62
1(CH <sub>3</sub> )-Y3	I	22.68	25	20.96	61.56	144
1(Br)-Y3	I	22.68	25	20.96	76.04	202
1[C]-P3	I	21.60	10	20.51	39.30	90
1[C]-Y3	I	21.30	10	20.48	37.62	77
1-[C]Y3	I	22.20	10	20.57	31.61	16
1[C]-[C]Y3	I	22.50	10	20.60	21.96	13
2-Y3	I	24.28	[25	21.40	41.99]	[34
2-Y5	I	25.50	25	21.48	42.72]	67
4-Y3	I	25.52				
4-OOCY4	I	28.74	25	22.48	50.01	91
20-P3	I	23.60	[10	20.86	40.64]	[102
20-P5	I	26.10				
20-Y3	I	23.70	[25	21.60	43.68]	[34
20-Y5	I	26.18				
[Py]-PO5	I	23.65	10	20.72	43.72	95
[Py]-[C]Y3	I	20.50	10	20.40	36.83	37
3[C]-Y2	M	23.45	[25	21.47	47.57]	[86
3[C]-Y4	M	25.75				
3[C]-[C]Y4	M	24.90	10	20.84	32.54	21
3Y-[C]4	M	25.65	10	20.92	33.75	32
4(CN)-Y3	M	25.52	10	20.90	48.19	177
5-[C]5	A	25.00	10	20.85	29.48	-9
20S[C]5	A	22.80	25	20.99	30.63	20
50S[C]4	A	25.80	25	21.74	35.18	35
NC-[C]5	A	21.85	25	20.76	38.69	54

<sup>a</sup>Extrapolated viscosity from effect of component when added to the RO-R' mixture HRL-2N42. <sup>b</sup>I = Table I in this paper, M = E. Merck, A = Atomergic Chemicals. <sup>c</sup>First mixture with 11.2% 2-Y3 and 13.8% 4-Y3; second mixture with 7.8% 2-Y3, 7.9% 2-Y5, and 9.4% 4-Y3. <sup>d</sup>Mixture with 3.9% 20-P3 and 6.1% 20-P5. <sup>e</sup>Mixture with 9.8% 20-Y3 and 15.2% 20-Y5. <sup>f</sup>Mixture with 11.2% 3[C]-Y2 and 13.8% 3[C]-Y4.

## VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

viscosity values of the additives at 25°C in the environment of the RO-R' host. Our comparisons are made assuming that each additive is accommodated by (or disrupts) the LC host similarly. Of course this is not strictly true, as is obvious, for example, in the case of the additive 5-[C]5 which gives a negative  $\eta_{\text{calc}}$  value. Nevertheless, we find that the  $\eta_{\text{class}}$  values assigned from these  $\eta_{\text{calc}}$  values (and from prior studies) give fairly accurate predictions for the  $\eta_{25^\circ\text{C}}$  of many multicomponent ester mixtures.<sup>1,2</sup> Thus, the  $\eta_{\text{class}}$  values are suitable for relative comparisons of LC structural effects on the flow viscosity.


### 3.3 Effects of Cyclohexane Rings

Table III shows the effects on the extrapolated component viscosity of replacing from one to three of the phenyl groups in 1-P3 with cyclohexyl groups, and of replacing one phenyl group in 1SP3 with a cyclohexyl ring. Each component in Table III has three rings in the same arrangement and has the same alkyl end groups, so that the only structural variation for each ester or thioester is the number and the position of the cyclohexyl groups. The clearpoint of these ester components vary between 126 and 204°C, but since only 10% of each is used in the HRL-2N42 the clearpoints of the mixtures which are used for the

viscosity measurements are not significantly different. The structural effects on viscosity in this series are apparent. The replacement of phenyl by cyclohexyl on the "alcohol" side of the ester linkage increases the viscosity:

e.g.  $1[C]-P3 > 1-P3$ ,  $1[C]-Y3 > 1-Y3$ , and  $1[C]-[C]Y3 > 1-[C]Y3$ . The substitution of a cyclohexyl ring for the outside phenyl ring on the biphenylcarboxylate side decreases the viscosity: e.g.  $1-Y3 < 1-P3$ , and  $1[C]-Y3 < 1[C]-P3$ . The thioester structure shows a similar effect, e.g. the viscosity of  $1SY3 < 1SP3$ . However, these effects are relatively small compared to the large decrease in  $\eta_{calc}$  resulting by replacement of both phenyls on the biphenylcarboxylate side with cyclohexyl rings: e.g.  $1-[C]Y3 \ll 1-P3$  (and  $1-Y3$ ), and  $1[C]-[C]Y3 \ll 1[C]-P3$  (and  $1[C]-Y3$ ).

Table III. Effect on Calculated Component Viscosity of Substituting Cyclohexyl For Phenyl Groups in 1-P3 and 1SP3.

Compound Code	Number of Cyclohexyls	Replacement Position of Cyclohexyl Groups			$\eta_{calc}$ . (cP, 25°C)
					
1-P3	0	---	---	---	81
1SP3	0	---	---	---	79
1[C]-P3	1	X	---	---	90
1-Y3	1	---	---	X	69
1SY3	1	---	---	X	62
1[C]-Y3	2	X	---	X	77
1-[C]Y3	2	---	X	X	16
1[C]-[C]Y3	3	X	X	X	19

The comparisons in Figure 1 confirm that there is in general a substantial decrease in class viscosity when a phenyl ring adjacent to ester carbonyl ("acid" side) is replaced by a cyclohexyl ring, e.g., when a benzoate group is

GROUP		GROUP	
CLASS STRUCTURE	$\eta_{\text{CLASS}}$	CLASS STRUCTURE	$\eta_{\text{CLASS}}$
	130		91
	82		54
	82		20
	67		16
	37		27
	36		16
	19		(0)

11

replaced by a cyclohexanecarboxylate group. A similar, but smaller decrease in  $\eta_{\text{class}}$  occurs in thio-ester structures: e.g.  $\text{ROS}[\text{C}]\text{R}' < \text{ROSR}'$ . Even when only one benzoate group is replaced in a diester structure, a large viscosity decrease is shown: e.g.  $\text{R-OOCYR}' < \text{R-OOCPR}'$ . Quite low  $\eta_{\text{class}}$  values are observed for the  $\text{R}[\text{C}]\text{YR}'$ ,  $\text{RO}[\text{C}]\text{R}'$ , and  $\text{R}[\text{C}]\text{R}'$  cyclohexanecarboxylate structures, each of whose LC compounds also have the advantage of having higher clearpoints than the corresponding benzoate compounds.

The effects on  $\eta_{\text{class}}$  of replacing a phenyl ester with a cyclohexyl ester are summarized in Figure 2. The  $\eta_{\text{class}}$  increases by an average of









 -OOC- GROUP		 -OOC- GROUP	
CLASS STRUCTURE	$\eta_{\text{CLASS}}$	CLASS STRUCTURE	$\eta_{\text{CLASS}}$
	81		90
	67		82
	16		20

FIGURE 2 Effect on class viscosity of replacing phenyl ester with a cyclohexyl ester.

## VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

about 20% when cyclohexyl replaces phenyl on the "alcohol" side of these structures.

The effects of replacing a biphenylcarboxylate group with a cyclohexylbenzoate group are summarized by the  $\eta_{\text{class}}$  comparisons in Figure 3. On the average this structural change decreases  $\eta_{\text{class}}$  by about 13%.

### 3.4 Effects of Ortho-Groups

The use of ortho-groups in LC structures is of













<div style="text-align: center;">  </div>		<div style="text-align: center;">  </div>	
CLASS STRUCTURE	$\eta_{\text{CLASS}}$	CLASS STRUCTURE	$\eta_{\text{CLASS}}$
	200		177
	102		94
	90		82
	81		67
	79		62

FIGURE 3 Effect on class viscosity of replacing a biphenylcarboxylate with a cyclohexylbenzoate group.

interest mainly as a means of altering the  $\Delta\epsilon$  and lowering the mp compared to the structure without the o-group. Among the o-groups whose viscosity effects are studied here, the o-Br, o-pyridyl, and o-CN groups give an increasingly strong negative  $\Delta\epsilon$  effect to their parent phenyl ester LC structures, while the o-CH<sub>3</sub> group increases the positive  $\Delta\epsilon$  of its parent structure.<sup>2</sup> However, one price paid for the lower mp and the altered  $\Delta\epsilon$  is that of a substantial increase in  $\eta_{\text{class}}$  of the o-group structures, as shown in Figure 4. The addition of an o-CN or o-Br group greatly increases the viscosity of a structure, generally more than doubling the  $\eta_{\text{class}}$ , while the presence of an o-pyridyl group causes a smaller viscosity increase. The addition of an o-CH<sub>3</sub> group strongly increases  $\eta_{\text{class}}$ , while an o-Cl group causes a smaller increase. In general the results shown in Figure 4 indicate that the increase of  $\eta_{\text{class}}$  due to the presence of o-groups is in approximately the following order: Br > CN > CH<sub>3</sub> > pyridyl > Cl.

#### 4. CONCLUSIONS

1. The replacement of phenyl rings by cyclohexyl rings in ester LC compounds alters their relative value of class viscosity, with the magnitude and the direction of the effect strongly


# VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

WITHOUT <i>o</i> -GROUP		WITH <i>o</i> -GROUP	
CLASS STRUCTURE	$\eta$ CLASS	CLASS STRUCTURE	$\eta$ CLASS
	180		310
			195
	130		153
	81		200
	67		202
			177
			144
	16		37

FIGURE 4 Effect on class viscosity of ortho-groups.

dependent upon the position of the cyclohexyl groups in the structure. When the class viscosities are extrapolated from viscosity measurements of the LC compounds as additives in a

standard host mixture of alkoxyphenyl alkylbenzoates, then for otherwise comparable structures the effects on  $\eta_{\text{class}}$  of replacing a phenyl ring with a cyclohexyl ring are typically as follows:



Thus, substitution of a cyclohexyl for a phenyl ring adjacent to the carbonyl group is by far the most effective way of using cyclohexyl rings to reduce the viscosity of ester LC structure.

2. Although o-groups can be used effectively to control the dielectric anisotropy contribution of component structures, and also to lower the melting point, this advantage is offset by a substantial increase in the class viscosity of a structure with an o-group as compared to the structure without it. In the present studies the presence of an o-group in a component increases the  $\eta_{\text{class}}$  value in the range of 20 to 200%. For these structures the magnitude of the o-group effect on  $\eta_{\text{class}}$  increases as follows:  
 $\text{Cl} < \text{pyridyl} < \text{CH}_3 < \text{CN} < \text{Br}.$

3. The assignment of class viscosities to LC ester structures is useful in comparing structural

## VISCOSITY OF ESTER LIQUID CRYSTAL COMPONENTS

effects of cyclohexyl rings and o-substituents on the relative viscosity contributions of ester and thioester LC compounds. The twenty  $\eta_{class}$  values assigned here along with the other eighteen assigned earlier,<sup>1</sup> can be used effectively to predict the flow viscosity of new multicomponent LC nematic mixtures.<sup>2,6</sup>

### 5. ACKNOWLEDGMENTS

This work was supported in part by the Office of Naval Research.

### REFERENCES

1. J. D. MARGERUM, S. -M. WONG, J. E. JENSEN and C. I. VAN AST, Liq. Cryst. and Ordered Fluids, A. C. Griffin and J. F. Johnson, Ed (Plenum Press, 1984), 4, p. 111.
2. J. D. MARGERUM, A. M. LACKNER, J. E. JENSEN, L. J. MILLER, W. H. SMITH, JR., S. -M. WONG, and C. I. VAN AST, Liq. Cryst. and Ordered Fluids, A. C. Griffin and J. E. Johnson, Eds. (Gordon and Breach) Vol. 5, in press.
3. J. D. MARGERUM, J. E. JENSEN and A. M. LACKNER, Mol. Cryst. Liq. Cryst., 68, 137 (1981).
4. J. D. MARGERUM, S. -M. WONG, A. M. LACKNER, Mol. Cryst. Liq. Cryst., 68, 157 (1981).

J. D. MARGERUM, S. -M. WONG, et al

5. J. D. MARGERUM and A. M. LACKNER, Mol. Cryst. Liq. Cryst., 76, 211 (1981).
6. A. M. LACKNER and J. D. MARGERUM, 10th International Liquid Crystal Conference, York, U. K. (1984).

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTEC/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Paul Delahay Department of Chemistry New York University New York, New York 10003	1	Dr. P. J. Hendra Department of Chemistry University of Southampton Southampton SO0 5NH United Kingdom	1
Dr. E. Yeager Department of Chemistry Case Western Reserve University Cleveland, Ohio 41106	1	Dr. Sam Perone Chemistry & Materials Science Department Laurence Livermore National Lab. Livermore, California 94550	1
Dr. D. N. Bennion Department of Chemical Engineering Brigham Young University Provo, Utah 84602	1	Dr. Royce W. Murray Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1
Dr. R. A. Marcus Department of Chemistry California Institute of Technology Pasadena, California 91125	1	Naval Ocean Systems Center Attn: Technical Library San Diego, California 92152	1
Dr. J. J. Auburn Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. C. E. Mueller The Electrochemistry Branch Materials Division, Research and Technology Department Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910	1
Dr. Adam Heller Bell Laboratories Murray Hill, New Jersey 07974	1	Dr. G. Goodman Johnson Controls 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1
Dr. T. Katan Lockheed Missiles and Space Co., Inc. P. O. Box 504 Sunnyvale, California 94088	1	Dr. J. Boechler Electrochimica Corporation Attn: Technical Library 2485 Charleston Road Mountain View, California 94040	1
Dr. Joseph Singer, Code 302-1 NASA-Lewis 21000 Brookpark Road Cleveland, Ohio 44135	1	Dr. P. P. Schmidt Department of Chemistry Oakland University Rochester, Michigan 48063	1
Dr. B. Brummer EIC Incorporated 55 Chapel Street Newton, Massachusetts 02158	1		
Library P. R. Mallory and Company, Inc. Northwest Industrial Park Burlington, Massachusetts 01803	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. H. Richtol Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1	Dr. R. P. Van Duyne Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. A. B. Ellis Chemistry Department University of Wisconsin Madison, Wisconsin 53706	1	Dr. B. Stanley Pons Department of Chemistry University of Alberta Edmonton, Alberta CANADA T6G 2G2	1
Dr. M. Wrighton Chemistry Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139		Dr. Michael J. Weaver Department of Chemistry Michigan State University East Lansing, Michigan 48824	1
Larry E. Plew Naval Weapons Support Center Code 30736, Building 2906 Crane, Indiana 47522	1	Dr. R. David Rauh EIC Corporation 55 Chapel Street Newton, Massachusetts 02158	1
S. Ruby DOE (STOR) 600 E Street Providence, Rhode Island 02192	1	Dr. J. David Margerum <del>Research Laboratories Division</del> <del>Hughes Aircraft Company</del> 3011 Malibu Canyon Road Malibu, California 90265	1
Dr. Aaron Wold Brown University Department of Chemistry Providence, Rhode Island 02192	1	Dr. Martin Fleischmann Department of Chemistry University of Southampton Southampton 509 5NH England	1
Dr. R. C. Chudacek McGraw-Edison Company Edison Battery Division Post Office Box 28 Bloomfield, New Jersey 07003	1	Dr. Janet Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. A. J. Bard University of Texas Department of Chemistry Austin, Texas 78712	1	Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1
Dr. M. M. Nicholson Electronics Research Center Rockwell International 3370 Miraloma Avenue Anaheim, California	1		

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Donald W. Ernst Naval Surface Weapons Center Code R-33 White Oak Laboratory Silver Spring, Maryland 20910	1	Mr. James R. Moden Naval Underwater Systems Center Code 3632 Newport, Rhode Island 02840	1
Dr. R. Nowak Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Bernard Spielvogel U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709	1
Dr. John F. Houlihan Shenango Valley Campus Pennsylvania State University Sharon, Pennsylvania 16146	1	Dr. Denton Elliott Air Force Office of Scientific Research Bolling AFB Washington, D.C. 20332	1
Dr. D. F. Shriver Department of Chemistry Northwestern University Evanston, Illinois 60201	1	Dr. David Aikens Chemistry Department Rensselaer Polytechnic Institute Troy, New York 12181	1
Dr. D. H. Whitmore Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Dr. A. P. B. Lever Chemistry Department York University Downsview, Ontario M3J1P3 Canada	1
Dr. Alan Bewick Department of Chemistry The University Southampton, SO9 5NH England		Dr. Stanislaw Szpak Naval Ocean Systems Center Code 6343 San Diego, California 95152	1
Dr. A. Himy NAVSEA-5433 NC #4 2541 Jefferson Davis Highway Arlington, Virginia 20362		Dr. Gregory Farrington Department of Materials Science and Engineering University of Pennsylvania Philadelphia, Pennsylvania 19104	1
Dr. John Kincaid Department of the Navy Strategic Systems Project Office Room 901 Washington, D.C. 20376		Dr. Bruce Dunn Department of Engineering & Applied Science University of California Los Angeles, California 90024	

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
M. L. Robertson Manager, Electrochemical and Power Sonics Division Naval Weapons Support Center Crane, Indiana 47522	1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. Elton Cairns Energy & Environment Division Lawrence Berkeley Laboratory University of California Berkeley, California 94720	1	Dr. D. Cipris Allied Corporation P. O. Box 3000R Morristown, New Jersey 07960	1
Dr. Micha Tomkiewicz Department of Physics Brooklyn College Brooklyn, New York 11210	1	Dr. M. Philpot IBM Corporation 5600 Cottle Road San Jose, California 95193	1
Dr. Lesser Blum Department of Physics University of Puerto Rico Rio Piedras, Puerto Rico 00931	1	Dr. Donald Sandstrom Washington State University Department of Physics Pullman, Washington 99164	1
Dr. Joseph Gordon, II IBM Corporation K33/281 5600 Cottle Road San Jose, California 95193	1	Dr. Carl Kannewurf Northwestern University Department of Electrical Engineering and Computer Science Evanston, Illinois 60201	1
Dr. Robert Somoano Jet Propulsion Laboratory California Institute of Technology Pasadena, California 91103	1	Dr. Edward Fletcher University of Minnesota Department of Mechanical Engineering Minneapolis, Minnesota 55455	1
Dr. Johann A. Joebstl USA Mobility Equipment R&D Command DRDME-EC Fort Belvoir, Virginia 22060	1	Dr. John Fontanella U.S. Naval Academy Department of Physics Annapolis, Maryland 21402	1
Dr. Judith H. Ambrus NASA Headquarters M.S. RTS-6 Washington, D.C. 20546	1	Dr. Martha Greenblatt Rutgers University Department of Chemistry New Brunswick, New Jersey 08903	1
Dr. Albert R. Landgrebe U.S. Department of Energy M.S. 6B025 Forrestal Building Washington, D.C. 20595	1	Dr. John Wassib Kings Mountain Specialties P. O. Box 1173 Kings Mountain, North Carolina 28086	1

TECHNICAL REPORT DISTRIBUTION LIST, 359

	<u>No.</u> <u>Copies</u>	<u>No.</u> <u>Copies</u>
Dr. J. J. Brophy University of Utah Department of Physics Salt Lake City, Utah 84112	1	
Dr. Walter Roth Department of Physics State University of New York Albany, New York 12222	1	
Dr. Thomas Davis National Bureau of Standards Polymer Science and Standards Division Washington, D.C. 20234	1	
Dr. Charles Martin Department of Chemistry Texas A&M University	1	
Dr. Anthony Sammells Institute of Gas Technology 3424 South State Street Chicago, Illinois 60616	1	
Dr. H. Tachikawa Department of Chemistry Jackson State University Jackson, Mississippi 39217	1	
Dr. W. M. Risen Department of Chemistry Brown University Providence, Rhode Island	1	

END

FILMED

8

74

DTIC